

EXTEC Abrasive Powders are formulated for use in distilled water mixtures and available in standard particle sizes and grades. Aluminum Oxide (Al_2O_3) and Silicon Carbide (SiC) Powders are recommended for fine grinding and rough polishing.

EXTEC Magnesium Oxide (MgO) is recommended when fine polishing wrought aluminum alloys and magnesium based metals and alloys.

EXTEC Iron Oxide (Fe_2O_3) is recommended to polish soft ores, glass, lapidary, and soft metals.

EXTEC Chromic Oxide (Cr_2O_3) is recommended when Aluminum Oxide contamination is not permissible.



CATALOG NUMBER	DESCRIPTION	UNIT
EXTEC Aluminum Oxide (Al_2O_3) Powder		
17012	3.0 μm	1 lb (.45 kg)
17016	3.0 μm	5 lb (2.3 kg)
17020	5.0 μm	1 lb (.45 kg)
17024	5.0 μm	5 lb (2.3 kg)
17028	9.5 μm	1 lb (.45 kg)
17032	9.5 μm	5 lb (2.3 kg)
17036	12.5 μm	1 lb (.45 kg)
17040	12.5 μm	5 lb (2.3 kg)
17044	14.5 μm	1 lb (.45 kg)
17048	14.5 μm	5 lb (2.3 kg)
17052	17.5 μm	1 lb (.45 kg)
17056	17.5 μm	5 lb (2.3 kg)
17060	20.0 μm	1 lb (.45 kg)
17064	20.0 μm	5 lb (2.3 kg)
17076	25.0 μm	1 lb (.45 kg)
17080	25.0 μm	5 lb (2.3 kg)
16836	240 Grit	1 lb (.45 kg)
16838	240 Grit	5 lb (2.3 kg)
16846	400 Grit	1 lb (.45 kg)
16848	400 Grit	5 lb (2.3 kg)
16852	600 Grit	1 lb (.45 kg)
16854	600 Grit	5 lb (2.3 kg)

CATALOG NUMBER	DESCRIPTION	UNIT
EXTEC Silicon Carbide (SiC) Abrasive Powder		
16802	120 Grit	1 lb (.45 kg)
16804	120 Grit	5 lb (2.3 kg)
16806	240 Grit	1 lb (.45 kg)
16808	240 Grit	5 lb (2.3 kg)
16812	320 Grit	1 lb (.45 kg)
16814	320 Grit	5 lb (2.3 kg)
16816	400 Grit	1 lb (.45 kg)
16818	400 Grit	5 lb (2.3 kg)
16822	600 Grit	1 lb (.45 kg)
16824	600 Grit	5 lb (2.3 kg)
16826	1000 Grit	1 lb (.45 kg)
16828	1000 Grit	5 lb (2.3 kg)
EXTEC Magnesium Oxide (MgO) Abrasive Powder		
16910	EXTEC Magnesium Oxide (MgO) Abrasive Powder	1 lb (.45 kg)
EXTEC Levigated Aluminum Oxide (Al_2O_3) Abrasive Powder		
16903	EXTEC Levigated Aluminum Oxide (Al_2O_3) Abrasive Powder 5 μm	1 lb (.45 kg)
16905		5 lb (2.3 kg)
EXTEC Iron Oxide (Fe_2O_3) Abrasive Powder		
16915	EXTEC Iron Oxide (Fe_2O_3) Abrasive Powder 3 μm	1 lb (.45 kg)
16918		5 lb (2.3 kg)
EXTEC Chromic Oxide (Cr_2O_3) Abrasive Powder		
16943	EXTEC Chromic Oxide (Cr_2O_3) Abrasive Powder 1-5 μm	1 lb (.45 kg)
16945		5 lb (2.3 kg)